





SCHOTT AR-Glas®

Tubing and Rod of Special Glass

SCHOTT

SCHOTT AR-Glas®: Tubing







Outside Diameter	Wall Thickness	Weight per Length (Length approx. 1500 mm)	Carton Contents	
 mm	 mm	 g	 Number of Tubes Weight approx. kg	
4	±0.10	0.50 ±0.02	21	582 12.0
	±0.10	0.70 ±0.03	27	551 15.0
	±0.13	0.90 ±0.03	33	548 18.0
5	±0.10	0.50 ±0.02	27	378 10.0
	±0.10	0.70 ±0.03	36	367 13.0
	±0.13	0.90 ±0.03	44	386 17.0
6	±0.10	0.50 ±0.02	33	618 20.0
	±0.10	0.70 ±0.03	44	252 11.0
	±0.10	0.90 ±0.03	54	278 15.0
7	±0.13	1.10 ±0.03	64	252 16.0
	±0.10	0.50 ±0.02	38	418 16.0
	±0.10	0.70 ±0.03	52	193 10.0
8	±0.10	0.90 ±0.03	65	186 12.0
	±0.13	1.10 ±0.03	77	196 15.0
	±0.10	0.50 ±0.02	44	340 15.0
9	±0.10	0.70 ±0.03	60	332 20.0
	±0.10	0.90 ±0.03	76	146 11.0
	±0.13	1.10 ±0.03	90	155 14.0
10	±0.13	0.50 ±0.02	50	280 14.0
	±0.13	0.70 ±0.03	69	278 19.0
	±0.13	0.90 ±0.03	86	255 22.0
11	±0.15	1.10 ±0.03	103	117 12.0
	±0.13	0.60 ±0.03	67	226 15.0
	±0.13	0.80 ±0.03	87	219 19.0
12	±0.15	1.00 ±0.03	106	208 22.0
	±0.15	1.20 ±0.04	125	97 12.0
	±0.13	0.60 ±0.03	74	163 12.0
13	±0.13	0.80 ±0.03	96	187 18.0
	±0.15	1.00 ±0.03	118	170 20.0
	±0.15	1.20 ±0.04	139	166 23.0
	±0.13	0.60 ±0.03	81	149 12.0
	±0.13	0.80 ±0.03	106	152 16.0
	±0.15	1.00 ±0.03	130	154 20.0
	±0.15	1.20 ±0.04	153	151 23.0
	±0.13	0.60 ±0.03	88	131 11.5
	±0.13	0.80 ±0.03	115	131 15.0
	±0.15	1.00 ±0.03	142	134 19.0
	±0.15	1.20 ±0.04	167	126 21.0



Can be ordered online*
www.schott.com/tubing/ecom

SCHOTT AR-Glas®: Tubing





Outside Diameter	Wall Thickness	Weight per Length (Length approx. 1500 mm)	Carton Contents	
 mm	 mm	 g	 Number of Tubes	Weight approx. kg
14	±0.13	0.60 ±0.03	95	211 20.0
	±0.13	0.80 ±0.03	125	113 14.0
	±0.15	1.00 ±0.03	154	111 17.0
	±0.15	1.20 ±0.04	182	111 20.0
15	±0.15	0.60 ±0.03	102	196 20.0
	±0.15	0.80 ±0.03	134	90 12.0
	±0.15	1.00 ±0.04	166	97 16.0
	±0.20	1.20 ±0.04	196	97 19.0
16	±0.15	0.60 ±0.03	109	165 18.0
	±0.15	0.80 ±0.03	144	168 24.0
	±0.15	1.00 ±0.04	177	85 15.0
	±0.20	1.20 ±0.04	210	86 18.0
17	±0.15	0.80 ±0.03	153	72 11.0
	±0.15	1.00 ±0.04	189	74 14.0
18	±0.20	0.80 ±0.03	163	135 22.0
	±0.20	1.00 ±0.04	201	70 14.0
	±0.20	1.20 ±0.04	238	67 16.0
	±0.25	1.50 ±0.05	293	69 20.0
19	±0.20	0.80 ±0.03	172	122 21.0
	±0.20	1.00 ±0.04	213	61 13.0
	±0.25	1.50 ±0.05	310	58 18.0
20	±0.20	0.80 ±0.04	182	100 18.0
	±0.20	1.00 ±0.04	224	103 23.0
	±0.20	1.20 ±0.05	267	56 15.0
21	±0.20	0.80 ±0.04	191	95 18.0
	±0.20	1.00 ±0.04	236	93 22.0
22	±0.20	0.80 ±0.04	201	80 16.0
	±0.20	1.00 ±0.04	248	89 22.0
	±0.20	1.20 ±0.05	295	82 24.0
23	±0.20	0.80 ±0.04	209	82 17.0
	±0.20	1.00 ±0.04	260	73 19.0
	±0.25	1.50 ±0.05	381	42 16.0



Can be ordered online*
www.schott.com/tubing/ecom



SCHOTT AR-Glas®: Tubing

Outside Diameter	Wall Thickness	Weight per Length (Length approx. 1500 mm)	Carton Contents	
 mm	 mm	 g	 Number of Tubes	Weight approx. kg
24	±0.20	1.00 ±0.04	74	20.0
	±0.20	1.20 ±0.05	65	21.0
	±0.25	1.50 ±0.05	38	15.0
25	±0.20	0.80 ±0.04	66	15.0
	±0.25	1.50 ±0.05	34	14.0
26	±0.20	1.00 ±0.04	58	17.0
	±0.25	1.20 ±0.05	63	22.0
	±0.25	1.50 ±0.05	32	13.8
28	±0.20	1.00 ±0.04	53	17.0
	±0.25	1.20 ±0.05	53	20.0
	±0.25	1.50 ±0.05	26	12.2
30	±0.25	1.20 ±0.05	42	17.1
	±0.30	1.50 ±0.06	42	21.1
32	±0.25	1.20 ±0.05	36	15.7
	±0.30	1.50 ±0.06	36	19.4
34	±0.25	1.20 ±0.05	30	13.9
	±0.30	1.50 ±0.06	30	17.2
36	±0.45	1.20 ±0.06	25	12.3
	±0.50	1.50 ±0.07	25	15.2
38	±0.45	1.20 ±0.06	25	13.0
	±0.50	1.50 ±0.07	25	16.1
40	±0.70	1.20 ±0.08	20	11.0
	±0.70	1.50 ±0.08	20	13.6







Can be ordered online*
www.schott.com/tubing/ecom

In addition to the above dimensions, other lengths and outside diameters up to 70 mm are available on request.

Tubing in the outside diameter range 5–30 mm can be coated for scratch protection (minimum order quantity 5 t). Order quantities of 1 t or more for outside diameters ≥ 10 mm can be supplied in DENSOPACK® packaging.

SCHOTT AR-Glas®: Rod¹⁾


Diameter		Carton Contents		Diameter		Carton Contents			
	mm		Number of Rods	Weight approx. kg		mm		Number of Rods	Weight approx. kg
3	±0.10	509	13.5	10	±0.25	49	14.4		
4	±0.15	308	14.5	12	±0.25	33	14.0		
5	±0.15	217	16.0	14	±0.30	24	13.8		
6	±0.15	141	15.0	16	±0.35	20	15.1		
7	±0.20	104	15.0	20	±0.50	16	18.8		
8	±0.20	79	15.0	25	±0.70	9	16.6		
9	±0.20	60	14.3						

¹⁾Rod length approx. 1500 mm

All dimensions of tubing and rod listed in this brochure are available at short notice. All carton contents and weights are approximate.



Can be ordered online*
www.schott.com/tubing/ecom





Clear Advantages: SCHOTT AR-Glas®

The Glass

AR-Glas® is a clear glass of Hydrolytic Class 3, and belongs to the soda lime group of glasses, with a high alkali and alkaline earth oxide content.

The Advantages

The outstanding properties of AR-Glas® are its multiple application possibilities, the good price/performance ratio, good workability and the accuracy of its dimensions. All the standard dimensions listed here are available at short notice.

The Quality

The quality of the products is ensured by the use of the most modern manufacturing technology and the DIN EN ISO 9001 quality assurance system, certified by TÜV certificate. The quality features are described in the relevant technical data sheets.

The Fields of Application

AR-Glas® has a wide range of applications, and is processed, for example, into pipettes, vials and test tubes. Many other laboratory articles and other technical products (e.g. solar collectors) are also made of AR-Glas®, and it is also used in the decorative glass industry for the manufacture of Christmas decorations.

The Manufacturer

Schott-Rohrglas manufactures special glass tubing, capillary and rod in a wide range of glass types and dimensions for a multitude of applications. With an annual production of approx. 65,000 tons, Schott-Rohrglas is one of the leading manufacturers of special glass tubing worldwide. Glass processors in more than 70 countries all over the world appreciate their long-standing experience, know-how and quality. Alongside the most modern melting and production methods for special glass, Schott-Rohrglas also offers the highest standards of precision in the processing sector: one of their particular talents lies in the field of highly-automatic finish grinding for tubing and rod in small diameters. In order to help you find the optimum solution, we would be pleased to work together with you and answer any questions you may have concerning further processing for glass tubing and rod.



SCHOTT AR-Glas®: Physical and Chemical Properties


Physical Data

Coefficient of mean linear thermal expansion α (20 °C; 300 °C) acc. to ISO 7991		$9.1 \cdot 10^{-6} \text{ K}^{-1}$
Transformation temperature T_g		525 °C
Temperature of the glass	10^{13} (annealing point)	530 °C
at viscosity η in dPa · s:	$10^{7.6}$ (softening point)	720 °C
	10^4 (working point)	1040 °C
Density ρ at 25 °C		$2.50 \text{ g} \cdot \text{cm}^{-3}$
Modulus of elasticity E (Young's modulus)		$73 \cdot 10^3 \text{ N} \cdot \text{mm}^{-2}$
Poisson's-Ratio μ		0.22
Thermal conductivity λ_w at 90 °C		$1.1 \text{ W} \cdot \text{m}^{-1} \cdot \text{K}^{-1}$
Temperature for the specific electrical resistance of $10^8 \Omega \cdot \text{cm}$ (DIN 52 326) t_{k100}		200 °C
Logarithm of the electric volume resistivity ($\Omega \cdot \text{cm}$)	at 250 °C	7.1
	at 350 °C	5.7
Dielectric properties (1 MHz, 25 °C)		
Dielectric constant (permittivity) ϵ		7.2
Dielectric loss factor (dissipation factor) $\tan \delta$		$70 \cdot 10^{-4}$
Refractive index ($\lambda = 587.6 \text{ nm}$) n_d		1.514
Stress-optical coefficient (DIN 52 314) K		$2.7 \cdot 10^{-6} \text{ mm}^2 \cdot \text{N}^{-1}$

Chemical Composition (main components in approx. weight %)

SiO ₂	B ₂ O ₃	K ₂ O	Al ₂ O ₃	Na ₂ O	BaO	CaO	MgO
69	1	3	4	13	2	5	3

Transmission



Resistance to Thermal Shock

Resistance to thermal shock is not an exactly defined physical value (for more details see ISO 718); it depends on the measuring method, the shape, the wall thickness and the surface and end properties of the glass object in question. Rapid temperature changes cause high temporary stress in the glass, meaning that rapid local cooling processes are very dangerous, since in this case a thin outer layer of the glass is placed under tensile stress over the still hot inner core. Glass is much more susceptible to tensile stress than to compressive stress.

Chemical Resistance

Hydrolytic Class (ISO 719)	HGB 3
Acid Class (DIN 12 116)	Class S 1
Alkali Class (ISO 695)	Class A 2



SCHOTT AR-Glas®: Technical Data

Outside Diameter and Wall Thickness

Outside diameter (OD) and wall thickness (WT) in accordance with the tables on pages 2–5.

In addition to the listed range, tubing with an OD of up to 70 mm and rod with a diameter of up to 30 mm, plus other wall thicknesses, are available on request.

Length

Standard lengths are as follows:


Tubing	1500 +5/-0 mm
Rod	1500 ± 20 mm

Special lengths from 1200 to 4000 mm for tubing in the outside diameter range from 18 to 38 mm are available on request.

Out-of-Round

Out-of-Round according to ISO 1101 depends on the nominal outside diameter OD. The following maximum values have been laid down:

OD	Maximum value t
< 25 mm	0.4 % of OD
25 – 35 mm	0.6 % of OD
> 35 mm	0.8 % of OD



Siding

Siding is the difference between the maximum and minimum wall thickness in a measured plane.


Wall thickness	Maximum values	
	Siding	
< 0.80 mm	6 % of the wall thickness	
≥ 0.80 mm	7 % of the wall thickness	



SCHOTT AR-Glas®: Technical Data

Straightness

Straightness according to ISO 1101 is based on the following maximum values:




OD	Maximum value t
4 – 6 mm	4.0 mm/1500 mm
> 6 mm	0.9 mm/1000 mm

Stress

Longitudinal stress	max. 4.0 MPa
Edge stress	max. 4.5 MPa

Stones and Knots

Stones are opaque inclusions, knots are transparent inclusions. Stones and knots with a core diameter of ≥ 0.5 mm are regarded as faults. (Detailed information on permissible faults, definition of faults, testing methods and testing units is available on request.)



Airlines

Airlines are an elongated, gaseous inclusion along the length of the tubing, which is generally not visible to the naked eye.

The aggregate airline length is defined by adding together the length of all airlines > 15 mm (or in the case of two or more overlapping airlines, the distance between the extremities of the airlines concerned). A cumulative airline length of > 1.00 m per 10 m of tubing is regarded as a fault. (Detailed information on permissible faults, definition of faults, testing methods and testing units is available on request.)





SCHOTT AR-Glas®:

Technical Data

Scratches

A scratch represents a slight surface defect which neither penetrates the depth of the wall, nor permeates it in any way and therefore has an insignificant effect on the mechanical stability.

Tubing of 5–30 mm outside diameter can be coated for protection against scratches.

End Finishes

Tubing ²⁾	
End finish: plain cut and fused	
Standard: vial fusing with a fusing thickness of 0.15 mm	
Other tubing end versions:	Fusing Thickness
Slightly fused	0.05 mm
Medium fusing	0.10 mm
Heavy fusing	0.20 mm
Rod	
Untreated	

²⁾ Other versions are also available on request.



Packaging

Standard: Cartons

On request: DENSOPACK®

Glass tubes are layered into bundles with a square or rectangular cross-section. They are packed into the geometrically tightest space and then covered at each end with transparent shrink film.

This means that no movement of the tubing is possible during transport, so that the pack is more stable and resilient. The shrink film at each end of the bundle closes each tube and provides the very best protection against contamination.

Technical Terms of Delivery

Detailed information on permissible faults, definition of faults, testing methods and testing units is available on request.



The Product Range

SCHOTT AR-Glas®

Special glass tubing (Hydrolytic Class 3) for the manufacture of pharmaceutical primary packaging (e.g. for solid oral medicines), for the field of medicine (e.g. disposables and pipettes) and for the cosmetic and food industries, tubing and rod for technical applications (e.g. solar collectors), and for the production of various glassblown products.

SCHOTT CONTURAX®

Special glass profiles for decorative and technical lighting, interior decorating, and use in commercial art; for further processing into perfume vials in the cosmetics industry.

SCHOTT DURAN®

Chemically and thermally highly resistant borosilicate glass tubing, capillary and rod (Hydrolytic Class 1) for a variety of applications, e.g. for the manufacture of glass apparatus, equipment and technical fittings; glass tubing and rod for special technical applications (e.g. explosion-proof light fittings, heat exchanger tubing, solar collectors), for processing into vials for medical and pharmaceutical applications and for the field of commercial art.

SCHOTT DURATAN®

Thermally prestressed (tempered) DURAN®. Thermal prestressing noticeably improves the shock resistance of the glass.

Main field of application: Explosion-proof light fittings.

SCHOTT DUROBAX®

Chemically highly resistant special glass tubing (Hydrolytic Class 1), especially suited for processing into pipettes, test tubes and glass syringes.

SCHOTT ESTAX® 8838

Special glass tubing (Hydrolytic Class 1) with especially low background radiation, e.g. for processing into scintillation vials for use in radiation measuring equipment.

SCHOTT FIOLAX®-clear and SCHOTT FIOLAX®-amber

Chemically highly resistant special glass tubing (Hydrolytic Class 1) for processing into ampoules, vials and other pharmaceutical primary packaging.

SCHOTT ILLAX®

Chemically highly resistant special glass tubing (Hydrolytic Class 2) for the manufacture of double tip ampoules, vials and other pharmaceutical primary packaging. ILLAX for technical application, e.g. for the production of adhesive anchors (glass dowels).

SCHOTT® N16B

Capillary and tubing of special glass type N16B for the manufacture of industrial, clinical and household thermometers. N16B is used for thermometers with a scale up to 430 °C and allows high precision temperature measurement. Schott-Rohrglas manufactures N16B capillary in a variety of designs.

Aluminosilicate Glasses

Special glass tubing which is resistant to high temperatures, is alkali-free and can be fused to molybdenum, used in particular for the production of halogen lamps for automotive and general lighting purposes.

Lead glasses

Electrically highly insulating with a low melting point, special glass tube cuttings are used for the hermetic sealing of semiconductors for the production of microdiodes and for electrotechnical applications.

In addition to these glass types we produce approx. 50 other special glasses – especially formulated to help you find solutions for your technical problems.

AR-Glas®, CONTURAX®, DENSOPACK®, DURAN®, DUROBAX®, DURATAN®, ESTAX®, FIOLAX® and ILLAX® are registered trademarks of Schott Group companies.

Subject to technical alteration.

We thank our customers for their kind assistance in providing product samples for the photos.

*For online orders from outside Europe please contact Schott-Rohrglas GmbH:
E-Mail silvia.gonzalvo@schott.com or by phone:
+49 (0) 96 33 / 80 - 2 72

Schott-Rohrglas GmbH
Erich-Schott-Strasse 14
P.O. Box 11 80
95660 Mitterteich
Germany
Phone: +49 (0) 96 33 / 80-0
Fax: +49 (0) 96 33 / 80-614
E-mail: info.tubing@schott.com
www.schott.com/tubing

SCHOTT